CEMINTEL

TECHNICAL DATA SHEET | CEMINTEL $^{\circledR}$ Street style edge cladding

APPLICATIONS	
	RESULT
Applications	Façades & Cladding, Internal Linings
Type of Building Structure	Residential Housing Buildings within the scope of AS4055
Wet Areas	No

PANEL - DIMENSIONAL & GEOMETRIC	CAL CHARACTERISTICS		
DIMENSIONAL/ GEOMETRICAL CHARACTERISTIC	SPECIFICATION	MANUFACTURING TOLERANCE	RELEVANT STANDARD
Panel Dimensions	1200mmW x 2450mmL x 9mmD - 75mm, 150mm, 400mm V-Groove, 150mm U-Groove	Width +0 -3 mm Length +0 -3 mm Thickness +0.5 -0 mm	
	1200mmW x 2750mmL x 9mmD - 75mm, 150mm, 400mm V-Groove, 150mm U-Groove		
	1200mmW x 3000mmL x 9mmD - 75mm, 150mm, 400mm V-Groove, 150mm U-Groove		
Profile	Shiplap		
Perpendicularity/squareness of edges	2mm/linear metre		
Weight (typical)	13.5kg/m2		
Layout Options	Vertical		
Jointing	Concealed		

PANEL - STRENGTH & MOISTURE RELATED PROPERTIES		
PHYSICAL PROPERTY	CAS NUMBER	PROPORTION
Modulus of Rupture (Wet)	> 9 MPa	AS2908.2
Modulus of Elasticity (Wet)	3-5 GPa	AS2908.2
Density (Oven Dry)	1280 kg/m3	AS2908.2
Water Vapor Diffusion	Not Required	Not Required
Water Tightness (24hrs)	No water droplet	AS2908.2
Water Absorption (Saturated – 48hrs)	30 wt%	ASTM C 1186
Moisture Content	7 wt%	ASTM C 1186
Moisture Movement (30-90% Humidity)	0.05%	ASTM C 1186

PANEL - OTHER DURABILITY/WEATHER RESISTANCE INDI	CATORS	
TEST	RESULT	RELEVANT STANDARD
Heat Rain	PASSED (25 Cycles)	AS2908.2
Freeze Thaw	PASSED (50 Cycles)	AS2908.2
Warm Water Resistance	PASSED (56 days)	AS2908.2
Soak Dry	PASSED (25 Cycles)	AS2908.2

CHARACTERISTIC	RESU	ILT	RELEV	ANT STANDARD
Finish	Prepr	imed		
Coating Type	Seale	r Type: Pigmented Sealer On	Face	
Colour Bodied	No			
Paint Type				
UV Resistance	N/A		N/A	
Formaldehyde Emission Rate	N/A		N/A	
VOC Emission Rate	N/A		N/A	
SPECTRAL REFLECTIVITY VALUES	SOLAR REFLECTANCE %	SOLAR ABSORPTION %	BASIX COLOUR	RELEVANT STANDARD
Edge™ Cladding Edge Ribbon				
Edge™ Cladding Bond				
Edge™ Cladding Oxford				
Edge™ Cladding York				
Edge™ Cladding Crown				
Formaldehyde Emission Rate				

CHARACTERISTIC	RESULT	RELEVANT STANDARD
Fire Resistance		
Combustibility	Suitable for use in applications where non-combustible materials are specified by the Deemed to Satisfy Provisions of the 2016 BCA Vol 1 Amendment 1 Clause C1.9 (2015 BCA Vol Clause C1.12)	
Fire Hazard Properties	Average Specific Extinction Area <250	AS 5637.1
Classification	Group 1	AS/NZ 3837
Thermal Conductivity		
Thermal Conductivity (λ-Factor)	≈ 0.2535 W/m.K	
Thermal Expansion Coefficient	0.005-0.01mm/mK	N/A
Acoustic Value		
Sound reduction (depends on construction)	N/A	N/A

SYSTEM SOLUTIONS			
CHARACTERISTIC	RESULT	RELEVANT STANDARD	
Within Scope of AS4055?	Yes		
Wind Loading - Residential housing buildings within the scope of AS4055	N1, N2, N3, N4, N5, N6, C1, C2, C3, C4		
Weatherproofing	Suitable for all building classes as set out in the BCA (ie 1&10, 2-9)	N/A	
Cyclonic Conditions	N/A	N/A	
Fire Resistance Limits (FRLs)	Up to 120/120/120	Refer to Gyprock® The Red Book™	
Bushfire Construction	BAL 29 (Construction for Bushfire Attack Level 29 for an external wall)	AS 3959-8	
Acoustic	Acoustic solutions of up to RW/RW+CTR 53/44 (CSR 5174) are detailed	Refer to Gyprock® The Red Book™	
Thermal	Thermal solutions of up to RT(sum)/RT(win) 2.6/2.9	Refer to Gyprock® The Red Book™	

FIXING	
CHARACTERISTIC	
Maximum Span (Stud Spacing)	Up to 600mm
Direct Fix	
Nail to Timber Frame	Yes
Screw to Timber Frame	No
Screw to Steel Frame	Yes
Cavity Fix	
Timber Frame	Yes
Steel Frame	Yes
Masonry Frame	No
Exposed Fasteners	
Screw	Yes
Rivet	No
Nail	Yes
Concealed Fasteners	
Clip	No
Countersunk Screw/Nail	No
Adhesive, Split Batten, etc.	No
Hidden by Overlapping Panel	No
Flush Jointed (Taped)	No

WARRANTY 25 YEARS